



FURNITURE

JANKA WOOD HARDNESS RATING

lbf = pounds of force

	1820 lbf	HICKORY	HARD
	1450 lbf	HARD MAPLE	
	1360 lbf	WHITE OAK	
	1320 lbf	ASH	
	1290 lbf	RED OAK	
	1010 lbf	WALNUT	MEDIUM HARD
	950 lbf	MAPLE	
	950 lbf	CHERRY	
	830 lbf	ELM	
	380 lbf	WHITE PINE	SOFT